

IN THE SPECIFICATION:

Please replace the 2nd paragraph, lines 9-21, page 42, with the following:

Finely particulate zinc oxide (product of C.I. Kasei Company, Ltd., trade name “Ultrafine Particle Zinc Oxide Nanotec”, average particle diameter: 20 nm) was used as polyvalent metal compound particles. A solution of a polyester-urethane resin (product of Sumika Bayer Urethane Co., Ltd., aqueous dispersion of polyester-urethane, trade name “~~Bihydrol~~ Bayhydrol PR240”; solvent: water) was used as a resin. A phosphate salt type surfactant produced by Marubishi Oil Chemical Co., Ltd. was used as a surfactant. These components were mixed so as to give the following composition, and the resultant mixture was finally mixed by means of an ultrasonic homogenizer to prepare Coating Liquid VII.